

Certificate No. 15966/GBBPAJ
Date: June 14, 2016



SUCOFINDO

Issuing Office:

Jl. Arteri Tol Cibitung No. 1, Cibitung Bekasi 17520, Indonesia
Phone/Facs: +62 21 88321176/88321166
Email: afakhrudin@sucofindo.co.id

REPORT OF ANALYSIS

The sample was submitted by client with the following identification :

CLIENT : SCG LIGHTWEIGHT CONCRETE INDONESIA, PT.
ADDRESS : Surya Cipta Industrial Estate.
Jl. Techno Kav. I – T 1 – 3, Kutamekar, Ciampel.
KARAWANG.
TYPE OF SAMPLE : SILICA SAND.
DATE OF RECEIVED : 07/06/2016.
TEST REQUIRED : Chemical Analysis.
DESCRIPTION OF SAMPLE : Form : Sand.
Weight/Volume : ± 0.96 kg.
Packing : Plastic bag.
SAMPLE IDENTIFICATION : Code : Banten NS.
DATE OF ANALYSIS : 07/06/2016 to 13/06/2016.
YOUR REFERENCE : PO No. : 4021002316.


Result:

Parameter	Unit	Results	Method
Iron Trioxide (Fe ₂ O ₃)	%	0.21	PO / MIN – BT / 01
Aluminium Trioxide (Al ₂ O ₃)	%	3.73	PO / MIN – BT / 01
Calcium Oxide (CaO)	%	Less than 0.01	PO / MIN – BT / 01
Magnesium Oxide (MgO)	%	0.01	PO / MIN – BT / 01
Manganese Dioxide (MnO ₂)	%	0.02	PO / MIN – BT / 01
Chromium Trioxide (Cr ₂ O ₃)	%	Less than 0.01	PO / MIN – BT / 01
Sodium Oxide (Na ₂ O)	%	0.63	PO / MIN – BT / 01
Potassium Oxide (K ₂ O)	%	0.90	PO / MIN – BT / 01
Silicon Dioxide (SiO ₂)	%	92.49	PO / MIN – BT / 01
Titanium Dioxide (TiO ₂)	%	0.10	PO / MIN – BT / 01
Loss On Ignition (LOI)	%	1.61	PO / MIN – BT / 01
Moisture Content (MC)	%, AR	0.34	PO / MIN – BT / 01

Note = AR (As Received Basis).

This Certificate/report is issued under our General Terms and Conditions, copy of which is available upon request or may be accessed at www.sucofindo.co.id

CBT5001059165010



2324062

SCI-2007A