

Certificate No. 05038/GBBPAJ
Date: February 23, 2016



Issuing Office:
Jl. Arteri Tol Cibitung No. 1, Cibitung Bekasi 17520, Indonesia
Phone/Facs: +62 21 88321176/88321166
Email: afakhrudin@sucofindo.co.id

REPORT OF ANALYSIS

The sample was submitted by client with the following identification :

CLIENT : SCG LIGHTWEIGHT CONCRETE INDONESIA, PT.
ADDRESS : Surya Cipta Industrial Estate.
Jl. Techno Kav. I – T 1 – 3, Kutamekar, Ciampel.
KARAWANG.
TYPE OF SAMPLE : GYPSUM.
DATE OF RECEIVED : 17/02/2016.
TEST REQUIRED : Chemical Analysis and pH.
DESCRIPTION OF SAMPLE : Form : Soil.
Weight/Volume : ± 1.55 kg.
Packing : Plastic bag.
SAMPLE IDENTIFICATION : Code: PIGMEN Penjernihan Air.
DATE OF ANALYSIS : 17/02/2016 to 23/02/2016.
YOUR REFERENCE : PO No. : 4021001833.


Result:

Parameter	Unit	Results	Method
Iron Trioxide (Fe ₂ O ₃)	%	0.07	ASTM C 471-01 (2006)
Aluminium Trioxide (Al ₂ O ₃)	%	0.03	ASTM C 471-01 (2006)
Magnesium Oxide (MgO)	%	0.04	ASTM C 471-01 (2006)
Manganese Dioxide (MnO ₂)	%	Less than 0.01	ASTM C 471-01 (2006)
Chromium Trioxide (Cr ₂ O ₃)	%	Less than 0.01	ASTM C 471-01 (2006)
Sodium Oxide (Na ₂ O)	%	0.01	ASTM C 471-01 (2006)
Potassium Oxide (K ₂ O)	%	Less than 0.01	ASTM C 471-01 (2006)
Silicon Dioxide (SiO ₂)	%	0.61	ASTM C 471-01 (2006)
Titanium Dioxide (TiO ₂)	%	Less than 0.01	ASTM C 471-01 (2006)
CaSO ₄ . ₂ H ₂ O	%	55.69	ASTM C 471-01 (2006)
Calcium Oxide (CaO)	%	18.13	ASTM C 471-01 (2006)
Sulfur Trioxide (SO ₃)	%	25.90	ASTM C 471-01 (2006)
Combine Water	%	11.66	ASTM C 471-01 (2006)
Free Moisture 45°C	%, AR	23.42	ASTM C 471-01 (2006)
pH	-	9.20	pH Metric

Note : AR (As Received Basis).

This Certificate/report is issued under our General Terms and Conditions, copy of which is available upon request or may be accessed at www.sucofindo.co.id

CBT5000332165010-001



2249788