

Test report 2.2

EN10204



06.05.2015/12:44:46
1/1

ECKART GMBH

Güntersthal 4, 91235 Hartenstein, Deutschland

PT. SCG LIGHTWEIGHT CONCRETE
INDONESIA

Surya Cipta City of Industry

Jl. Surya Tekno Kav. I-T1-3

41361 KARAWANG, JAWA BARAT

customer no.

119306

order no.

10067124

customer order no.

4021000760

order date

24.03.2015

delivery

80092330

Our laboratory has carried out tests and obtained the following results:

article-no.	article description	batch no.	quantity
053606PX0	Stapa Alupor N 700 Aluminium 800 kg = 32 PE bags of 25 kg	1145370001	3.200,000 KG

insp. characteristic	specification	nominal value	unit
Ti00004 volatile content	28,0 - 32,0	29,3	%
Ti00004 pigment content / non volatile	68,0 - 72,0	70,7	%
Ti00120 active metal content	>= 92	93	%
Ti00030 sieving < 71 µm	>= 97,5	99,9	%
Wet Screen Analysis with Water			
Ti00030 sieving < 45 µm	92,0 - 97,0	95,4	%
Wet Screen Analysis with Water			

ECKART GmbH
quality control department

This document has been printed automatically and will not be signed.

ECKART GmbH
Güntersthal 4
91235 Hartenstein
Tel +49 9152 77-0
Fax +49 9152 77-7008
info.eckart@altana.com
www.eckart.net

Vorsitzender des
Aufsichtsrats
Dr. Matthias L. Wolfgruber
Geschäftsführer
Dr. Wolfgang Schütt (Vors.)
Jürgen Gerbig
Sabine Rupp

Handelsregister und Sitz
Sitz: Hartenstein
Amtsgericht Nürnberg
HRB-Nr. 25736
USt-ID-Nr. DE 132744965

Bankverbindungen für EUR Zahlungen
und alle Währungen
Commerzbank Fürth
Kto-Nr. 160 22 00
BLZ 762 400 11
Swift COBADEFF762
IBAN DE10 7624 0011 0160 2200 00

Bankverbindung nur für USD
Deutsche Bank Nürnberg
Kto-Nr. 722 007 200
BLZ 760 700 12
Swift DEUTDEMM760
IBAN DE54 7607 0012 0722 0072 00

Test report 2.2

EN10204



06.05.2015/12:44:42
1/1

ECKART GMBH

Güntersthal 4, 91235 Hartenstein, Deutschland

PT. SCG LIGHTWEIGHT CONCRETE
INDONESIA

Surya Cipta City of Industry
Jl. Surya Tekno Kav. I-T1-3
41361 KARAWANG, JAWA BARAT

customer no. 119306
order no. 10067124
customer order no. 4021000760
order date 24.03.2015
delivery 80092330

Our laboratory has carried out tests and obtained the following results:

article-no.	article description	batch no.	quantity
053606PX0	Stapa Alupor N 700 Aluminium 800 kg = 32 PE bags of 25 kg	1132816001	3.200,000 KG

insp. characteristic	specification	nominal value	unit
TI00004 volatile content	28,0 - 32,0	29,8	%
TI00004 pigment content / non volatile	68,0 - 72,0	70,2	%
TI00120 active metal content	>= 92	95	%
TI00030 sieving < 71 µm Wet Screen Analysis with Water	>= 97,5	99,8	%
TI00030 sieving < 45 µm Wet Screen Analysis with Water	92,0 - 97,0	96,1	%

ECKART GmbH
quality control department

This document has been printed automatically and will not be signed.

ECKART GmbH
Güntersthal 4
91235 Hartenstein
Tel +49 9152 77-0
Fax +49 9152 77-7008
info.eckart@altana.com
www.eckart.net

Vorsitzender des
Aufsichtsrats
Dr. Matthias L. Wolfgruber
Geschäftsführer
Dr. Wolfgang Schütt (Vors.)
Jürgen Gerbig
Sabine Rupp

Handelsregister und Sitz
Sitz: Hartenstein
Amtsgericht Nürnberg
HRB-Nr. 25736
UST-ID-Nr. DE 132744965

Bankverbindungen für EUR Zahlungen
und alle Währungen
Commerzbank Fürth
Kto-Nr. 160 22 00
BLZ 762 400 11
Swift COBADEFF762
IBAN DE10 7624 0011 0160 2200 00

Bankverbindung nur für USD
Deutsche Bank Nürnberg
Kto-Nr. 722 007 200
BLZ 760 700 12
Swift DEUTDEMM760
IBAN DE54 7607 0012 0722 0072 00

Test report 2.2

EN10204

06.05.2015/12:44:44
1/1

ECKART GMBH

Güntersthal 4, 91235 Hartenstein, Deutschland

PT. SCG LIGHTWEIGHT CONCRETE
INDONESIA

Surya Cipta City of Industry

Jl. Surya Tekno Kav. I-T1-3

41361 KARAWANG, JAWA BARAT

customer no.

119306

order no.

10067124

customer order no.

4021000760

order date

24.03.2015

delivery

80092330

Our laboratory has carried out tests and obtained the following results:

article-no.	article description	batch no.	quantity
053606PX0	Stapa Alupor N 700 Aluminium 800 kg = 32 PE bags of 25 kg	1145369001	4.000,000 KG

insp. characteristic	specification	nominal value	unit
T100004 volatile content	28,0 - 32,0	29,1	%
T100004 pigment content / non volatile	68,0 - 72,0	70,9	%
T100120 active metal content	>= 92	94	%
T100030 sieving < 71 µm Wet Screen Analysis with Water	>= 97,5	99,8	%
T100030 sieving < 45 µm Wet Screen Analysis with Water	92,0 - 97,0	96,1	%

ECKART GmbH
quality control department

This document has been printed automatically and will not be signed.

ECKART GmbH
Güntersthal 4
91235 Hartenstein
Tel +49 9152 77-0
Fax +49 9152 77-7008
Info.eckart@altana.com
www.eckart.net

Vorsitzender des
Aufsichtsrats
Dr. Matthias L. Wolfgruber
Geschäftsführer
Dr. Wolfgang Schütt (Vors.)
Jürgen Gerbig
Sabine Rupp

Handelsregister und Sitz
Sitz: Hartenstein
Amtsgericht Nürnberg
HRB-Nr. 25736
USt-ID-Nr. DE 132744965

Bankverbindungen für EUR Zahlungen
und alle Währungen
Commerzbank Fürth
Kto-Nr. 160 22 00
BLZ 762 400 11
Swift COBADEFF762
IBAN DE10 7624 0011 0160 2200 00

Bankverbindung nur für USD
Deutsche Bank Nürnberg
Kto-Nr. 722 007 200
BLZ 760 700 12
Swift DEUTDEMM760
IBAN DE54 7607 0012 0722 0072 00

Test report 2.2

EN10204



06.05.2015/12:44:46
1/1

ECKART GMBH

Güntersthal 4, 91235 Hartenstein, Deutschland
PT. SCG LIGHTWEIGHT CONCRETE
INDONESIA
Surya Cipta City of Industry
Jl. Surya Tekno Kav. I-T1-3
41361 KARAWANG, JAWA BARAT

customer no. 119306
order no. 10067124
customer order no. 4021000760
order date 24.03.2015
delivery 80092330

Our laboratory has carried out tests and obtained the following results:

article-no.	article description	batch no.	quantity
053606PX0	Stapa Alupor N 700 Aluminium 800 kg = 32 PE bags of 25 kg	1145370001	3.200,000 KG

insp. characteristic	specification	nominal value	unit
TI00004 volatile content	28,0 - 32,0	29,3	%
TI00004 pigment content / non volatile	68,0 - 72,0	70,7	%
TI00120 active metal content	>= 92	93	%
TI00030 sieving < 71 µm Wet Screen Analysis with Water	>= 97,5	99,9	%
TI00030 sieving < 45 µm Wet Screen Analysis with Water	92,0 - 97,0	95,4	%

ECKART GmbH
quality control department

This document has been printed automatically and will not be signed.

ECKART GmbH
Güntersthal 4
91235 Hartenstein
Tel +49 9152 77-0
Fax +49 9152 77-0008
info.eckart@altana.com
www.eckart.net

Vorsitzender des
Aufsichtsrats
Dr. Matthias L. Wolfgruber
Geschäftsführer
Dr. Wolfgang Schütt (Vors.)
Jürgen Gerbig
Sabine Rupp

Handelsregister und Sitz
Sitz: Hartenstein
Amtsgericht Nürnberg
HRB-Nr. 25736
USI-ID-Nr. DE 132744965

Bankverbindungen für EUR Zahlungen
und alle Währungen
Commerzbank Fürth
Kto-Nr. 160 22 00
BLZ 762 400 11
Swift COBADEFF762
IBAN DE10 7624 0011 0160 2200 00

Bankverbindung nur für USD
Deutsche Bank Nürnberg
Kto-Nr. 722 007 200
BLZ 760 700 12
Swift DEUTDEMM760
IBAN DE54 7607 0012 0722 0072 00

Test report 2.2

EN10204



06.05.2015/12:44:46
1/1

ECKART GMBH

Güntersthal 4, 91235 Hartenstein, Deutschland

PT. SCG LIGHTWEIGHT CONCRETE
INDONESIA

Surya Cipta City of Industry
Jl. Surya Tekno Kav. I-T1-3
41361 KARAWANG, JAWA BARAT

customer no. 119306
order no. 10067124
customer order no. 4021000760
order date 24.03.2015
delivery 80092330

Our laboratory has carried out tests and obtained the following results:

article-no.	article description	batch no.	quantity
053606PX0	Stapa Alupor N 700 Aluminium 800 kg = 32 PE bags of 25 kg	1145370001	3.200,000 KG

insp. characteristic	specification	nominal value	unit
Ti00004 volatile content	28,0 - 32,0	29,3	%
Ti00004 pigment content / non volatile	68,0 - 72,0	70,7	%
Ti00120 active metal content	>= 92	93	%
Ti00030 sieving < 71 µm Wet Screen Analysis with Water	>= 97,5	99,9	%
Ti00030 sieving < 45 µm Wet Screen Analysis with Water	92,0 - 97,0	95,4	%

ECKART GmbH
quality control department

This document has been printed automatically and will not be signed.

ECKART GmbH
Güntersthal 4
91235 Hartenstein
Tel +49 9152 77-0
Fax +49 9152 77-7008
info.eckart@altana.com
www.eckart.net

Vorsitzender des
Aufsichtsrats
Dr. Matthias L. Wolfgruber
Geschäftsführer
Dr. Wolfgang Schütt (Vors.)
Jürgen Gerbig
Sabine Rupp

Handelsregister und Sitz
Sitz: Hartenstein
Amtsgericht Nürnberg
HRB-Nr. 25736
USt-ID-Nr. DE 132744965

Bankverbindungen für EUR Zahlungen
und alle Währungen
Commerzbank Fürth
Kto-Nr. 160 22 00
BLZ 762 400 11
Swift COBADEFF762
IBAN DE10 7624 0011 0160 2200 00

Bankverbindung nur für USD
Deutsche Bank Nürnberg
Kto-Nr. 722 007 200
BLZ 760 700 12
Swift DEUTDEMM760
IBAN DE54 7607 0012 0722 0072 00