

Certificate No. 32720/GBBPAN Date: September 17, 2020



Jl. Arteri Tol Cibitung No. 1, Cibitung Bekasi 17520, Indonesia Phone/Facs: +62 21 88321176/88321166 Email: afakhrudin@sucofindo.co.id Issuing Office:

## REPORT OF ANALYSIS

The sample was submitted by client with the following identification:

CLIENT

SCG LIGHTWEIGHT CONCRETE INDONESIA, PT.

**ADDRESS** 

Jl. Surya Tekno Kav. I - T1 - 3,

Suryacipta City Of Industry, Kutamekar, Ciampel.

KARAWANG 41361.

TYPE OF SAMPLE

SILICA SAND.

DATE OF RECEIVED

27/08/2020.

TEST REQUIRED

Chemical Analysis.

DESCRIPTION OF SAMPLE

Form

: Sand.

Weight/Volume: ± 1.73 kg.

Packing

: Plastic bag.

neral

ulianto

SAMPLE IDENTIFICATION

Code: Babel KTP.

DATE OF ANALYSIS

27/08/2020 to 11/09/2020.

YOUR REFERENCE

PO No.: 4021009784.

## Result:

Parameter	Unit	Results	Method
Iron Trioxide (Fe <sub>2</sub> O <sub>3</sub> )	%	0.16	ICP ICP
Aluminium Trioxide (Al <sub>2</sub> O <sub>3</sub> )	%	0.21	ICP
Calcium Oxide (CaO)	%	0.08	ICP
Magnesium Oxide (MgO)	%	Less than 0.01	ICP
Manganese Dioxide (MnO <sub>2</sub> )	%	Less than 0.01	ICP
Chromium Trioxide (Cr <sub>2</sub> O <sub>3</sub> )	%	0.03	ICP
Sodium Oxide (Na <sub>2</sub> O)	%	0.01	ICP
Potassium Oxide (K <sub>2</sub> O)	%	0.01	ICP
Silicon Dioxide (SiO <sub>2</sub> )	%	99.05	ICP
Titanium Dioxide (TiO <sub>2</sub> )	%	0.16	ICP
Loss On Ignition (LOI)	%	0.13	Gravimetric
Moisture Content (MC)	%, AR	1.88	Gravimetric

Note: AR (As Received Basis).

"This the result (s) related to the sample (s) submitted only and the report/certificate cannot be reproduced in any way, except in full context and with the prior approval in writing from Sucofindo Laboratory. This Certificate/report is issued under our General Terms and Conditions, copy of which is available upon request or may be accessed at www.sucofindo.co.id".

110650000267



01-2007A